

tasa 642-HCL
3162-St-sti**CLEAN COPY OF THE CLAIMS SHOWING AMENDMENTS**

1. Hot-melt pressure-sensitive adhesive based one or more non-thermoplastic elastomers, comprising
 - at least 100 parts by mass of one or more non-thermoplastic elastomers,
 - from 1 to [200] 100 parts by mass of one or more tackifying resins,
 - from 1 to 100 parts by mass of one or more reactive phenolic resins, for the
chemical/thermal crosslinking of the hot-melt pressure-sensitive adhesive, whose
methylol content is from 1 to 20% by weight based on the reactive phenolic resin, and
optionally from 1 to 100 parts by mass of accelerator substances.